



US008071160B2

(12) **United States Patent**
Chinn et al.

(10) **Patent No.:** **US 8,071,160 B2**
(45) **Date of Patent:** ***Dec. 6, 2011**

(54) **SURFACE COATING PROCESS**

(75) Inventors: **Jeffrey D. Chinn**, Foster City, CA (US);
Robert W. Ashurst, Auburn, AL (US);
Adam N. Anderson, Moseley, VA (US)

(73) Assignee: **Integrated Surface Technologies**,
Menlo Park, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 749 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/115,874**

(22) Filed: **May 6, 2008**

(65) **Prior Publication Data**

US 2009/0110819 A1 Apr. 30, 2009

Related U.S. Application Data

(60) Provisional application No. 61/029,801, filed on Feb. 19, 2008, provisional application No. 60/983,504, filed on Oct. 29, 2007.

(51) **Int. Cl.**

B05D 5/12 (2006.01)
H05K 3/00 (2006.01)
C23C 16/00 (2006.01)

(52) **U.S. Cl.** **427/96.6**; 427/96.2; 427/97.5;
427/96.8; 427/126.4; 427/126.3; 427/204;
427/205; 427/220; 427/255.29; 427/255.31;
427/255.37; 427/419.2; 439/43

(58) **Field of Classification Search** 427/96.6,
427/407.1, 189, 96.2, 96.5, 126.1, 126.2,
427/126.4; 349/149; 977/720, 722, 779,
977/782

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,913,827 B2 * 7/2005 George et al. 428/402
7,258,895 B2 * 8/2007 Sandhu 427/255.28
2002/0025446 A1 * 2/2002 Chen et al. 428/543
2007/0141114 A1 * 6/2007 Muisener et al. 424/427
2007/0275411 A1 * 11/2007 McGall et al. 435/7.1
2008/0304008 A1 * 12/2008 Muisener et al. 351/159

OTHER PUBLICATIONS

Boulinos et al., "Clay-Organosiloxane Hybrids: A Route to Cross-Linked Clay Particles and Clay Monoliths", Chem. Mater. 2004, vol. 16, pp. 2404-2410.*

Ashurt et al., "Vapor Phase Anti-Stiction Coatings for MEMS", EEE Transactions on Device and Materials Reliability, vol. 3, No. 4. Dec. 2003, pp. 173-179.*

* cited by examiner

Primary Examiner — Dah-Wei Yuan

Assistant Examiner — Jose Hernandez-Diaz

(74) *Attorney, Agent, or Firm* — Microtechnology Law & Analysis; Daniel L. Flamm

(57) **ABSTRACT**

A method of forming a film is provided. Nanoparticles are deposited on a surface of a substrate using a liquid deposition process. The nanoparticles are linked to each other and to the surface using linker molecules. A coating having a surface energy of less than 70 dyne/cm is deposited over the film to form a coated film. The coated film has an RMS surface roughness of 25 nm to 500 nm, a film coverage of 25% to 60%, a surface energy of less than 70 dyne/cm; and a durability of 10 to 5000 microNewtons. Depending on the particular environment in which the film is to be used, a durability of 10 to 500 microNewtons may be preferred. A film thickness 3 to 100 times the RMS surface roughness of the film is preferred.

5 Claims, 17 Drawing Sheets

